Declaration of Conformity

We,



Polma Matrassenfabriek Zilverhoek 13 4651 SP Steenbergen The Netherlands

declare under our sole responsibility that our product:

Polma Poseidon

- Item: MED/3.21 Bedding components
- Mattress with removable cover
- Fabric: 100% Polyester FR
- Filling: Pocket Springs 7 comfort-zones + Fire Retardant, eco-friendly cold foam HR50
- Dimensions: Any thickness between 19 and 25 cm, any size

to which this declaration relates, conforms to the following standard(s) or normative document(s):

- IMO 2010 FTP Code Annex 1 Fire test procedures Part 9 (Smouldering cigarette test)
- IMO 2010 FTP Code Annex 1 Fire test procedures Part 9 (Match flame equivalent)
- ISO 6330 (2021) (Washing and drying)
- EC TYPE EXAMINATION (module B) CERTIFICATE Nr. MED_2022_0001_B Expiry date: 14/03/2027 Standard: The revised FTP Code adopted by resolution MSC.307(88) (2010 FTP Code) Annex 1 Part 9: Bedding components
 EC QUALITY SYSTEM (module D) CERTIFICATE Nr. MED_2022_0002_D
- Expiry date: 14/03/2025 Standard: Marine Equipment Directive 2014/90/EC, with the type described in the EC Type Examination Certificate(s) (Module B).

This product has been assigned a:

U.S. Coast Guard Module B number 164.142/EC0493/2022_0001 (Expiry date: 14/03/2027)

This products carries the Wheelmark:



which was first affixed in 2023 by Centexbel, notitified body nr. 0493.

Place: Steenbergen, NL

Signature:

Dennis van Heiningen Company Director Polma Matrassenfabriek Date: 15/03/2023



EC TYPE EXAMINATION (module B) CERTIFICATE

Nr. MED_2022_0001_B

Expiry date: 14/03/2027

Name and address applicant:

POLMA Matrassenfabriek Zilverhoek 13 4651SP Steenbergen Nederland

Item: MED/3.21 Bedding components

Product Designation: Mattress with removable cover

Matras Polma Marine Fabric: 100% Polyester FR Filling: Bonnell Springs + Richfoam Polyether FR SG30

Specific Standard:

- The revised FTP Code adopted by resolution MSC.307(88) (2010 FTP Code) Annex 1 Part 9: Bedding components

This product has been assigned a **U.S. Coast Guard Module B number 164.142/EC0493 XXX** to note type approval to Module B only as it pertains to obtaining US Coast Guard approval as allowed by the "Agreement between the European Community and the United States of America on Mutual Recognition of Certificates of Conformity for Marine Equipment" signed February 27th, 2004

The above described article must be provided with the wheel mark in accordance with the rules laid out article 10 and annex I of the Directive 2014/90/EU.



0493/YY 0493: Notified body number undertaking surveillance module yy: last two digits of year mark affixed





The mark shall be affixed to the equipment (together with the name and address of the manufacturer and type designation) or to its data plate so as to be visible, legible and indelible throughout the anticipated useful life of the equipment.

Name and address manufacturer:

POLMA Matrassenfabriek Zilverhoek 13 4651SP Steenbergen Nederland

Type Examination documentation:

This declaration applies to the equipment submitted in the type testing and described in the manufacturer's technical file (Module B) that is registered with the number MED_2022_0001_B.

This certificate has been drawn up in accordance with the general certification regulation of Centexbel which is available via <u>http://www.Centexbel.be</u>

Issued by Centexbel, notified body 0493^(*), in Ghent, on March 14th 2022

Inge De Witte Certification Manager

Centexbel

Notified Body N°: 0493

Annex: 1 pages

Note 1. This certificate will not be valid if the manufacturer makes any changes or modifications to the approved equipment, which have not been notified to, and agreed with the notified body named on this certificate.

Note 2. Should the specified regulations or standards be amended during the validity of this certificate, the product(s) is/are to be re-approved prior to it/they being placed on board vessels to which the amended regulations or standards apply.

Note 3. The Mark of Conformity may only be affixed to the above type approved equipment and a Manufacturer's Declaration of Conformity issued when the production control phase module (D, E or F) of ANNEX II of the Directive is fully complied with and controlled by a written inspection agreement with a notified body.

Note 4. In case limitations of use apply, these should be indicated of in the Annex.





GENT • Technologiepark 70 • BE 9052 Gent • Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be **VAT** • BE 0459.218.289 • **IBAN** • BE 44 2100 4729 6545 • **BIC** • GEBABEBB



Annex to the certificate: Nr. MED_2022_0001_B

Approval documentation

Article	Report Nr. Centexbel	Composition
Matras Polma Marine	21.07349.01	Fabric: 100% Polyester FR
		Filling: Bonnell Springs + Richfoam Polyether FR SG30





EC QUALITY SYSTEM (module D) CERTIFICATE

Nr. MED_2022_0002_D

Expiry date: 14/03/2025

Name and address manufacturer:

POLMA Matrassenfabriek Zilverhoek 13 4651SP Steenbergen Nederland

Centexbel did undertake the relevant quality assessment procedures for the equipment of the manufacturer identified below which was found to be in compliance with the requirements of the Marine Equipment Directive 2014/90/EC, with the type described in the EC Type Examination Certificate(s) (Module B) listed in the Attachment to this certificate.

Item: MED/3.21 Bedding components

The manufacturer is allowed to affix the **U.S. Coast Guard approval number** (see annex) as allowed by the "Agreement between the European Community and the United States of America on Mutual Recognition of Certificates of Conformity for Marine Equipment" signed February 27th, 2004

This certificate authorises the manufacturer or his authorised representative established within the Community in conjunction with the EC TYPE EXAMINATION (module B) CERTIFICATE of the equipment listed in the scope to affix the wheel mark in accordance with the rules laid out in the article 10 and annex I of the Directive 2014/90/EC.



0493/YY 0493: Notified body number undertaking surveillance module yy: last two digits of year mark affixed





The mark shall be affixed to the equipment (together with the name and address of the manufacturer and type designation) or to its data plate so as to be visible, legible and indelible throughout the anticipated useful life of the equipment.

This certificate loses its validity if the manufacturer makes any changes or modifications to the approved quality system, which have not been notified to, and agreed with the notified body named on this certificate and/or after lapse of time, withdrawal or revocation of the EC Type Examination (Module B) Certificate.

This certificate has been drawn up in accordance with the general certification regulation of Centexbel which is available via <u>http://www.Centexbel.be</u>

Issued by Centexbel, notified body 0493^(*), in Ghent, on 14 March 2022

Certification Manager

Centexbel Notified Body N°: 0493

Annex: 1 page

Notes. This certificate authorises the manufacturer or his authorised representative established within the Community in conjunction with the EC TYPE EXAMINATION (MODULE B) CERTIFICATE of the equipment listed in the scope to affix the "Mark of Conformity" (wheelmark). This certificate loses its validity if the manufacturer makes any changes or modifications to the approved quality system, which have not been notified to, and agreed with the notified body named on this certificate and/or after lapse of time, withdrawal or revocation of the EC Type Examination (Module B) Certificate.





Annex to EC QUALITY SYSTEM (MODULE D) CERTIFICATE Nr. MED_2022_0002_D

Module B	ltem	USCG Approval number	Expiry date	Notified
				Body
MED_2022_0001_B	MED/3.21	164.142/EC0493/2022_0001	14/03/2027	0493



CENTEXBEL • textile competence centre • www.centexbel.be GENT • Technologiepark 70 • BE 9052 Gent • Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be VAT • BE 0459.218.289 • IBAN • BE 44 2100 4729 6545 • BIC • GEBABEBB



Polma Matrassenfabriek Zilverhoek 13 **4651SP STEENBERGEN Netherlands**

Your notice of 07-02-2023

Your reference

Date 28-02-2023



Required tests : IMO - 2010 FTP Code Annex 1 -Fire test procedures - Part 9 IMO - 2010 FTP Code Annex 1 -Fire test procedures - Part 9 ISO 6330 (2021)

Fire tests - Test for bedding components - smouldering cigarette test Fire tests - Test for bedding components - Match flame

equivalent Washing and drying

Sample id	Information given by the client	Date of receipt
T2302985	Polma Poseidon - 19 cm	07-02-2023
T2302986	Polma Poseidon - 25 cm	07-02-2023

WICH

Petra Wittevrongel Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be Digitally signed by Centexbel VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Analysis Report 23.00725.01 Date 28-02-2023 Page 2/17

Reference: T2302985 - Polma Poseidon - 19 cm

IMO bedding components

Information given by the client

Type of material Removable cover Mattress yes

Fabric

Composition Structure Thickness in mm Weight g/m² Colour Inherently FR treated

Filling

Material

Density Fire retardant treatment 100% Polyester FR Knitted X 300 Natural + Natural yes

Toplayer: NA50038 Naturalis High Resilience Fire Retardant (3cm) Core: Pocket spring 50 kg/m³ yes



Reference: T2302985_02s - Polma Poseidon - 19 cm - filling

Fire tests - Test for bedding components - smouldering cigarette test

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Information given by the client	Identical sides
Dimension of the specimens	2000 mm x 785 mm x 185 mm
Ignition source: smouldering cigarette with the following specifications Length: (70 ± 4) mm	

Length: (70 ± 4) mm Diameter: (8.0 ± 0.5) mm Mass: (0.95 ± 0.15) g Smouldering rate: (11.0 ± 4.0) min / 50 mm

in f



Cigarettes on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
More than 25 mm from edge of cotton wool	no	no
(horizontal)		
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurence of flames	no	no
Additional observations		
Maximum extent of damage from the edge	35	30
of cotton wool (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

f

0)



Reference: T2302985_02s - Polma Poseidon - 19 cm - filling

Fire tests - Test for bedding components - Match flame equivalent

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Information given by the client	Identical sides
Dimension of the specimens	2000 mm x 785 mm x 185 mm
Flame application time (s)	20

in f



Flame on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smouldering more than 25 mm from source	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
> 66% consumed	no	no
Burning to the extremities	no	no
Burning through thickness	no	no
Flaming > 150 s	no	no
Afterflame time (s)	0	1
Additional observations		
Afterglow time (s)	0	0
Maximum extent of damage from the	5	10
ignition source (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

f

0)



Reference: T2302985_01s - Polma Poseidon - 19 cm - cover

Washing and drying

Date of ending the test Standard used	17-02-2023 ISO 6330 (2021)
Deviation from the standard Conditioning Apparatus Used detergent Washing method and temperature Drying method Number of washing cycles	20°C, relative humidity 65% Wascator FOM 71 (type A) ECE detergent (Type 3) 4N- 40°C (2021) A = Line dry after each washing cycle (2021) 3
Mass of the test specimens Mass of the ballast	1981 g The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2302985_03d

in f



Reference: M2303531 T2302985_02s - Polma Poseidon - 19 cm - filling T2302985_03d - Polma Poseidon - 19 cm - washed cover

Fire tests - Test for bedding components - smouldering cigarette test

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Removable cover	yes
Information given by the client	Identical sides
Dimension of the specimens	2000 mm x 785 mm x 205 mm
Ignition source: smouldering cigarette with the following specifications Length: (70 ± 4) mm Diameter: (8.0 ± 0.5) mm Mass: (0.95 ± 0.15) g Smouldering rate: (11.0 ± 4.0) min / 50 mm	

in



Test 1 - cigarette on upper surface

Test 2 - cigarette in the groove of the quilt-line

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
More than 25 mm from edge of cotton wool	no	no
(horizontal)		
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurence of flames	no	no
Additional observations		
Maximum extent of damage from the edge	20	20
of cotton wool (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

in f



Reference: M2303531 T2302985_02s - Polma Poseidon - 19 cm - filling T2302985_03d - Polma Poseidon - 19 cm - washed cover

Fire tests - Test for bedding components - Match flame equivalent

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Removable cover	yes
Information given by the client	Identical sides
Dimension of the specimens	2000 mm x 785 mm x 205 mm
Flame application time (s)	20

in f



Test 1 - Flame on upper surface

Test 2 - Flame in the groove of the quilt-line

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smouldering more than 25 mm from source	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
> 66% consumed	no	no
Burning to the extremities	no	no
Burning through thickness	no	no
Flaming > 150 s	no	no
Afterflame time (s)	0	0
Additional observations		
Afterglow time (s)	0	0
Maximum extent of damage from the	10	10
ignition source (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

in

f



Analysis Report 23.00725.01 Date 28-02-2023 Page 12/17

Reference: T2302986 - Polma Poseidon - 25 cm

IMO bedding components

Information given by the client

Type of material Removable cover Mattress yes

Fabric

Composition Structure Thickness in mm Weight g/m² Colour Inherently FR treated

Filling

Material

Density Fire retardant treatment 100% Polyester FR Knitted X 300 Natural + Natural yes

Toplayer: NA50038 Naturalis High Resilience Fire Retardant (5cm) Core: Pocket spring 50 kg/m³ yes



Reference: T2302986_02s - Polma Poseidon - 25 cm - filling

Fire tests - Test for bedding components - smouldering cigarette test

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9	
Deviation from the standard	-	
Conditioning	23°C, relative humidity 50%	
Information given by the client	Identical sides	
Dimension of the specimens	2000 mm x 785 mm x 220 mm	
Ignition source: smouldering cigarette with the following specifications Length: $(70 + 4)$ mm		

Length: (70 ± 4) mm Diameter: (8.0 ± 0.5) mm Mass: (0.95 ± 0.15) g Smouldering rate: (11.0 ± 4.0) min / 50 mm

in f



Cigarettes on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
More than 25 mm from edge of cotton wool	no	no
(horizontal)		
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurence of flames	no	no
Additional observations		
Maximum extent of damage from the edge	25	35
of cotton wool (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

f

0)



Reference: T2302986_02s - Polma Poseidon - 25 cm - filling

Fire tests - Test for bedding components - Match flame equivalent

Date of ending the test Standard used	27-02-2023 IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 9
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Information given by the client	Identical sides
Dimension of the specimens	2000 mm x 785 mm x 220 mm
Flame application time (s)	20

in f



Flame on the smooth surface (no stitchings)

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smouldering more than 25 mm from source	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
> 66% consumed	no	no
Burning to the extremities	no	no
Burning through thickness	no	no
Flaming > 150 s	no	no
Afterflame time (s)	0	0
Additional observations		
Afterglow time (s)	0	0
Maximum extent of damage from the	10	10
ignition source (mm)		
Conclusion	non-ignition	non-ignition

Conclusion Not readily ignitable - Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

f

0)



Sample history

T2302985_01sPolma Poseidon - 19 cm - coverSplit sample from T2302985 (Polma Poseidon - 19 cm)

spirt sample from 12502985 (Forma Foseidon - 19 cm)

T2302985_02sPolma Poseidon - 19 cm - fillingSplit sample from T2302985 (Polma Poseidon - 19 cm)

T2302985_03dPolma Poseidon - 19 cm - washed coverFrom sample T2302985_01s and the following procedure (Polma Poseidon - 19 cm - cover)Washing and drying

Date of ending the test Standard used	17-02-2023 ISO 6330 (2021)
Deviation from the standard Conditioning Apparatus Used detergent Washing method and	- 20°C, relative humidity 65% Wascator FOM 71 (type A) ECE detergent (Type 3) 4N- 40°C (2021)
temperature Drying method Number of washing cycles	A = Line dry after each washing cycle (2021) 3
Mass of the test specimens Mass of the ballast	1981 g The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

T2302986_02s Polma Poseidon - 25 cm - filling

Split sample from T2302986 (Polma Poseidon - 25 cm)

M2303531

Sample composed of T2302985_02s (Polma Poseidon - 19 cm - filling) T2302985_03d (Polma Poseidon - 19 cm - washed cover)